
PRODUCT DATA SHEET

POLYKICK™ ACCELERATOR

PTI ADDITIVES

DESCRIPTION

POLYKICK™ is an additive specifically formulated by Products Techniques Inc. for our Polyurethane top coats. This product speeds up dry times but does not affect the rate of a full chemical. Although formulated for use with our Polyurethane coatings, PolyKick™ will work with most two component polyurethane system.

COATING PROPERTIES & CHARACTERISTICS

| | |
|----------------------------------|-------------|
| Flash Point | 116°F |
| Weight (lbs per gallon) | 7.2 lbs |
| Color | Clear |
| Volatile Organic Compounds (VOC) | 959 g/l |
| Specifications | Proprietary |

SHELF LIFE

Shelf life is only applicable for materials stored in unopened and undamaged original factory filled containers. 1 year when stored between 50°-85° Fahrenheit.

MIXING INSTRUCTIONS

Shake PolyKick for 1 – 2 minutes for optimal results. Add PolyKick to the Polyurethane Topcoat according to the instructions below.

At 1% by weight added to admixed material:

Tack free: 1 hour

Dry hard: 1.5 hours

Material jelled: 2.5 hours

At 5% by weight added to admixed material:

Tack free: 20 minutes

Dry hard: 30 minutes

Material jelled: 45 minutes

Do not add more than 5%. Addition of more than 5% may adversely affect the quality of the cured topcoat.

HEALTH, SAFETY, & STORAGE REQUIREMENTS

Refer to each individual material SDS (Safety Data Sheet) for specific requirements on the health, safety, storage and handling requirements. Follow all local, state, and national regulations during surface preparation, material application and cleanup.

PRODUCT DATA SHEET

PRODUCT INFORMATION & DISCLAIMER

Product Data Sheets are periodically updated to reflect new information. It is important to use the latest and most recent revision for the product being used. The foregoing information is accurate to the best of our knowledge. However, due to differences in customer handling, use and method of application which are not known and are beyond our control, Products Techniques, Inc. makes no warranties as to the end result.